

TIS® 800-20-07 The series of products are highly efficient insulating products and they also have thermal conductivity. It achieves the effect of both insulation and heat conduction by adding insulating silicone base material to the heat-conducting material.

Features

- » High thermal conductive and High dielectric strength
- » Low thermal resistance with high voltage isolation
- » Resistant to tears and punctures

Application

- » Car Battery & Power Supply
- » Power semiconductors
- » Audio and Video components
- » Motor controllers

Typical Properties of TIS® 810-20-07

Property	Value	Test method
colour	Green	Visual
Construction	Ceramic filled silicone elastomer / Fiberglass	-
Thickness range (inch/mm)	0.010/0.254	ASTM D374
Density (g/cc)	2.4	ASTM D297
Breaking Strength (MPa)	47	ASTM D1458
Recommended Operating Temperature (° C)	-60~180	-
Breakdown Voltage (V/mm)	6000	ASTM D149
Dielectric Constant @1000Hz	7.0	ASTM D150
Volume Resistivity (Ohm-cm)	1x10 ¹³	ASTM D257
Thermal Conductivity (W/mK)	2.0	ASTM D5470
	2.0	ISO22007-2.2
Thermal impedance (°C·in ² /W) @30psi	0.40	ASTM D5470
Flame Rating	V-0	UL94 (E331100)

Product Specification

Standard thickness: 0.010inch(0.254mm).


Standard size:

12" * 160' (304 mm * 48.76 m).

The TIS series can be die-cut into different shapes and provided. If you need different thicknesses, please contact our company.

Product Identifier

TIS8 10 - 20- 07



Global solutions:Local support

China:+86-769-38801208
Taiwan:+886-2-2277-1007
Canada:+001-604-2998559
Vietnam:+84-396852859

service@ziitek.com
www.ziitek.com

Ziitek Technology Ltd and its distributors provide information deemed accurate and reliable. However, product specifications may be adjusted due to technical modifications or optimizations without prior notice. The responsibility for product use and application lies with the end user. Ziitek makes no guarantees regarding the product's suitability, merchantability, or fitness for a particular purpose and assumes no liability for incidental or consequential damages. Ziitek and its logo are the property of the company or its affiliates.



TIS800-20-07-0425